

SYLVACOTE™ 4985 Modified Rosin Ester

PRODUCT DATA SHEET

SYLVACOTE 4985 modified rosin ester binder enables pavement marking formulators to reduce TiO₂ use in thermoplastic traffic striping formulations because binder color remains low during melting and application. Markings can be formulated with SYLVACOTE 4985 to deliver long lasting visibility with reduced cost-in-use.

FEATURES

- Light initial color with good color stability
- Good adhesion with glass-beads, anti-skid aggregates and the pavement
- Initial and long term retro-reflectivity
- Adhesion to damp substrates
- Oil & gas resistance
- Produced from a purified pine feedstock and formulated to a controlled specification
- Based on a renewable, non-food, non-animal raw material

POTENTIAL APPLICATION

- Spray- or screed-applied thermoplastic traffic striping
- Preformed thermoplastic pavement marking
- Thermoplastic pavement marking tape

SALES SPECIFICATIONS

Property	Test Method* (Kraton method)	Specification	Typical Value
Softening Point (°C)	ASTM E28-99 (AQCM 003)	100 - 110	106
Color, Gardner, 50wt% in toluene	ASTM D6166 (AQCM 002)	Max. 6	2.5
Acid value (mg KOH/g)	ASTM D465 (AQCM 001)	30 - 45	37

*Kraton internal methods are based on referenced standard method. Guidance is available upon request.

TYPICAL VALUES

Property	Test Method* (Kraton method)	Typical Value	
Glass Transition Temperature (°C)	Internal method (AQCM 218)	55	
Flashpoint (°C)	ASTM D92 (AQCM 007)	>250	
Viscosity (mPa.s)	ASTM D2196 (AQCM 004)	135°C	9900
		150°C	2400
		180°C	325
		200°C	126

*Kraton internal methods are based on referenced standard method. Guidance is available upon request.

<p>SOLUBILITY</p>	<p>SYLVACOTE 4985 is soluble in:</p> <ul style="list-style-type: none"> - Aromatic / aliphatic solvents like hexane & toluene - Esters and ketones like ethylacetate and acetone - Long chain alcohols like pentanol <p>Insoluble in alcohols and water.</p>
<p>COMPATIBILITY</p>	<p>SYLVACOTE 4985 can be plasticized with mineral oil, vegetable oil or tall oil esters and is compatible with:</p> <ul style="list-style-type: none"> - Hot melt polyamides - Most commonly used EVA copolymers - Polyethylene waxes - Natural rubber & synthetic rubber (SIS, SBR and SBS)
<p>PACKAGING</p>	<p>SYLVACOTE 4985 is delivered as pastilles in 25 kg bags or 500 and 1000 kg bulk bags.</p>
<p>STORAGE RECOMMENDATION</p>	<p>To preserve product quality, storage and transit dry and below 25°C/ 77°F is recommended. To prevent remassing, keep away from direct sun light or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use.</p>

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVACOTE are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016-2017 Kraton Corporation

March 2017

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com