

SYLVALITE™ RE 88F Rosin Ester

PRODUCT DATA SHEET

SYLVALITE RE 88F rosin ester is a very light and stable glycerol ester with a medium softening point. This resin is compatible with a broad range of polymers, which enables formulation flexibility in various hot melt and solvent based adhesive applications. This rosin ester is especially suitable for pressure sensitive adhesive tapes and labels application. The low Tg of SYLVALITE RE 88F rosin ester provides enhanced performance at lower temperatures.

FEATURES:

- Light color
- Broad compatibility
- Low Tg

POTENTIAL APPLICATIONS:

- Packaging
- PSA tapes & labels
- Flooring

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point (°C)	AQCM 003	85 - 92	88
Color (Gardner, 1:1 toluene)	AQCM 002	Max. 3	1.2
Acid Number (mg KOH/g)	AQCM 001	2-8	5

*Kraton test methods are available upon request

TYPICAL PROPERTIES

Property	Test Method*	Typical Value
Glass Transition Temperature (°C)	AQCM 218	41
Viscosity, Brookfield (125°C), cps.	AQCM 004	3068
Viscosity, Brookfield (150°C), cps.		379
Viscosity, Brookfield (177°C), cps.		85

*Kraton test methods are available upon request

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com

SOLUBILITY	<p>SYLVALITE RE 88F rosin ester is soluble in:</p> <ul style="list-style-type: none"> - Aromatic and aliphatic solvents like hexane & toluene - Esters and ketones like ethyl acetate and acetone - Long chain alcohols like butanol and pentanol
COMPATIBILITY	<p>SYLVALITE RE 88F rosin ester is compatible with:</p> <ul style="list-style-type: none"> - Ethylene Vinyl Acetate (EVA) - Ethylene Butyl Acrylate (EBA) - Styrene-Isoprene-Styrene (SIS) - Styrene-Butadiene-Styrene (SBS) - SB rubber - Natural rubber - Acrylic polymers
PACKAGING	<p>SYLVALITE RE 88F rosin ester is delivered in pastille form in 25kg bags.</p>
STORAGE RECOMMENDATION	<p>To preserve product quality, cool storage and transit at (<70 °F / 20 °C) is recommended. To prevent remassing, keep away from direct sunlight or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use. Due to its low Tg, do not stack pallets on top of each other during storage. Mild remassing or compaction of the product that is readily broken apart is not considered a basis for rejection of the product.</p>

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVALITE are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com