

SYLVARES™ 520 AMS Phenolic Resin

PRODUCT DATA SHEET

SYLVARES 520 AMS (alpha methyl styrene) Phenolic resin is a water white aromatic hydrocarbon resin with good oxidative stability. The phenolic component improves compatibility with high polarity polymers. The low Tg of SYLVARES 520 resin improves elasticity at low temperature.

FEATURES:

- Waterwhite color
- Contains polar groups
- Low Tg

POTENTIAL APPLICATIONS:

- Packaging
- Bookbinding
- Woodworking

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point (°C)	AQCM 003	70-80	75
Color, (Hazen, 1:1 toluene)	AQCM 002	Max. 60	26

*Kraton test methods are available upon request

TYPICAL VALUES

Property	Test Method*	Typical Value
Glass Transition Temperature (°C)	AQCM 218	38
Viscosity, Brookfield (125°C), cps.	AQCM 004	1069
Viscosity, Brookfield (150°C) cps.		193
Viscosity, Brookfield (177°C) cps.		57

*Kraton test methods are available upon request

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com

SOLUBILITY	SYLVARES 520 AMS Phenolic resin is soluble in: <ul style="list-style-type: none"> - aromatic solvents like toluene - esters and ketones like ethyl acetate and acetone - insoluble in aliphatic solvent like hexane and in alcohols like ethanol and propanol
COMPATIBILITY	SYLVARES 520 AMS Phenolic resin is compatible with: <ul style="list-style-type: none"> - styrene phase of SBCs - ethylene co-polymers like EVA with 28 to 45 % VA - higher polarity polymers like polyurethane - paraffin, microcrystalline, FT and polyethylene waxes
PACKAGING	The product is a solid resin supplied as pastilles in 20kg and 500kg paper bags.
STORAGE RECOMMENDATION	To preserve product quality, cool storage and transit at (< 70°F / 20°C) is recommended. To prevent remassing, keep away from direct sunlight or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVARES are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation

Contact us:

Almere (NL): +31 (0)36 54 62 800
Savannah (US): + 1 (912) 238-6439
Shanghai (CN): + 86 21 6434 8898
www.kraton.com