

UNI-REZ™ 111 Polyamide Resin

PRODUCT DATA SHEET

UNI-REZ 111 polyamide resin is an alcohol soluble type resin that is used for flexographic printing. It has balanced properties making it a good choice for general purpose flexographic surface printing.

FEATURES

- Mid-range viscosity
- Alcohol soluble
- Highly compatible with nitrocellulose

POTENTIAL APPLICATIONS:

- Good balance of viscosity and film properties
- Balance of solvent release and gel resistance
- Good heat resistance

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point, Ring & Ball, °C	AQCM 003A	123-133	125
Color, 50% in n-Propanol, Gardner	AQCM 002C	Max. 7	6
Acid Number	AQCM 001	Max. 6	5.1
Amine Number	AQCM 069A	Max. 7	5.0
Solution Viscosity Brookfield, 50% in n-Propanol	AQCM 004	175-215	209

*Kraton test methods are available upon request

TYPICAL VALUES

Property	Test Method*	Typical Value
Solution Viscosity Brookfield, 40% in n-Propanol, 25°C	AQCM 004	75
Zahn cup #2 elution time (sec.), 40% in n-Propanol, 25°C	AQCM 145	30
Viscosity, Brookfield, cps 160°C	AQCM 004	470
Color, 40% in n-Propanol, Gardner	AQCM 002A	5 +

*Kraton test methods are available upon request

DOT SHIPPING CLASSIFICATION	Not regulated as dangerous goods.
PACKAGING	UNI-REZ 111 is a granulated resin, packaged in multiwall paper bags, 25 kg, 500 kg per a pallet and 500Kg big bags are also available.
STORAGE RECOMMENDATION	Granulated forms of resin are prone to slow oxidation which may result in darkening and/or have an adverse effect on solubility after prolonged storage. The shelf life of this product can be extended by storing in full, closed containers kept in a cool, dry area.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and UNI-REZ are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com