

UNI-REZ™ 2940 Polyamide Resin

PRODUCT DATA SHEET

UNI-REZ 2940 polyamide resin is a co-solvent type resin which is soluble in alcohols, but typically requires mixtures of aliphatic hydrocarbons and alcohols for gel stability. UNI-REZ 2940 polyamide resin provides fast solvent release and good grease resistance in flexographic / gravure inks for plastic substrates and is especially effective as an overprint lacquer.

FEATURES:

- Fast solvent release
- Co-solvent type polyamide
- Good grease, ice-pack, water and chemical resistance

POTENTIAL APPLICATIONS:

- Used for flexographic ink on plastic substrates
- Lowest viscosity co-solvent resin
- Can be used for overprint lacquers, especially cold seal release lacquers

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Acid Number	AQCM 001	1-6	1.8
Amine Number	AQCM 069A	Max. 7	3.7
Viscosity, Brookfield, cps 160°C	AQCM 004	1200-1800	1280
Color, 35% in Toluene/ n-Butanol, Gardner	AQCM 002C	Max. 7	5
Softening Point, Ring & Ball, °C	AQCM 003A	105-115	111
Solution Viscosity Brookfield, 35% in Toluene /n-Butanol, 25°C	AQCM 004	50-80	65

*Kraton test methods are available upon request

TYPICAL VALUES

Property	Test Method*	Typical Value
Solution Viscosity Brookfield, 35% in i-Propanol/VM&P Naphtha, 25°C	AQCM 004	93
Zahn cup #2 elution time (sec.), 35% in i-Propanol/VM&P Naphtha, 25°C	AQCM 145	37
Viscosity, Brookfield, cps 160°C	AQCM 004	1417
Color, 35% in i-Propanol/VM&P Naphtha, Gardner	AQCM 002A	5

*Kraton test methods are available upon request

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com

DOT SHIPPING CLASSIFICATION	Not regulated as dangerous goods.
PACKAGING	UNI-REZ 2940 is a granulated resin, packaged in multiwall paper bags, 50lbs. net.
STORAGE RECOMMENDATION	Granulated forms of resin are prone to slow oxidation which may result in darkening and/or have an adverse effect on solubility after prolonged storage. The shelf life of this product can be extended by storing in full, closed containers kept in a cool, dry area.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and UNI-REZ are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation

Contact us:
Almere (NL): +31 (0)36 54 62 800
Savannah (US): + 1 (912) 238-6439
Shanghai (CN): + 86 21 6434 8898
www.kraton.com