

UNI-TAC™ 70 Rosin Tackifier

PRODUCT DATA SHEET

UNI-TAC 70 rosin tackifier is a modified rosin, which offers an excellent combination of oxidation and crystallization resistance. This product functions as a tackifier for SBR, natural rubber, butyl rubber, ethylene-vinyl acetate and other polymers.

FEATURES:

- Good tack and stability
- No tendency to crystallize
- Oxidation resistant

POTENTIAL APPLICATIONS:

- Flooring
- Construction
- PSA tape & label
- Sealants
- Hot melt applications
- Rubber compounding

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point (°C)	AQCM 003	75 - 85	80
Color (Gardner, 50% in toluene)	AQCM 002	Max 14	11+
Acid Number (mg KOH/g)	AQCM 001	145 – 160	155

*Kraton test methods are available upon request

TYPICAL VALUES

Property	Test Method*	Typical Value
Glass Transition Temperature (°C)	AQCM 218	33
Viscosity, Brookfield (125°C), cps.	AQCM 004	765
Viscosity, Brookfield (150°C), cps.		115
Viscosity, Brookfield (177°C), cps.		35

*Kraton test methods are available upon request

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com

SOLUBILITY	UNI-TAC 70 rosin tackifier is soluble in: <ul style="list-style-type: none"> - Aromatic and aliphatic hydrocarbon solvents, like hexane and toluene - Chlorinated solvents
COMPATIBILITY	UNI-TAC 70 rosin tackifier is compatible with: <ul style="list-style-type: none"> - Ethylene Vinyl Acetate (EVA) - Ethylene Butyl Acrylate (EBA) - Styrene-Isoprene-Styrene (SIS) - Styrene-Butadiene-Styrene (SBS) - SB Rubber - Natural rubber, Butyl rubber, Neoprene - Acrylic polymers, phthalate and polyester plasticizers - Alkyds and hydrocarbon resins
PACKAGING	UNI-TAC 70 rosin tackifier is available in pastille form in multi-wall bags, 50 lb. net or in molten bulk.
STORAGE RECOMMENDATION	This product is subject to remassing under all storage conditions. Product stored or transported at temperatures above 70 °F / 20 °C should be evaluated for impact on performance before use. Due to its low Tg, do not stack pallets on top of each other during storage. Remassing or compaction of the product that is readily broken apart is not considered a basis for rejection of this product.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and UNI-TAC are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com